






TEST REPORT

No. NKAQ20052589

Page 1 of 3

Name of Customer	NINGBO TIANSHENG WEBBING CO.,LTD	Specification/model	---
Address	---	Trademark	---
Manufacturer	---	Characteristics	Finished
Name of sample	EAR LOOP	Level	---
Tel	13282255648	Category of safety specification	---
Art.No.	---		
Above-mentioned information by Customer-supplied			
Form of sample receipt	Delivery	Sample quantity	1
Receiving Date of Sample	2020-5-26	Test Category	Consigned test
Test Requirements	GB/T 32610-2016、 FZ/T 01095-2002、 FZ/T 01057-2007		
Test result	<p>The details of test results have been printed on the next page.</p> <p style="text-align: right;">2020-6-1 Date of issue</p>		
Remarks	All the test items in this report were carried out under the environmental conditions stipulated by the corresponding standards.		



Approved by  Verified by  Typed by 

TEST REPORT

No. NKAQ20052589

Page 2 of 3

Items	Unit	Requirements	Results	Conclusions
Cleavable Arylamines (Banned Azo Dyes)	4-aminobiphenyl	mg/kg	N.D.	Pass
	benzidine	mg/kg	N.D.	
	4-chloro-o-toluidine	mg/kg	N.D.	
	2-naphthylamine	mg/kg	N.D.	
	o-aminoazotoluene	mg/kg	N.D.	
	5-nitro-o-toluidine	mg/kg	N.D.	
	p-chloroaniline	mg/kg	N.D.	
	2,4-diaminoanisole	mg/kg	N.D.	
	4,4'-diaminobiphenylmethane	mg/kg	N.D.	
	3,3'-dichlorobenzidine	mg/kg	N.D.	
	3,3'-dimethoxybenzidine	mg/kg	N.D.	
	3,3'-dimethylbenzidine	mg/kg	Banned (Limits: 20)	
	3,3'-dimethyl-4,4'-diaminobiphenylmethane	mg/kg	N.D.	
	p-cresidine	mg/kg	N.D.	
	4,4'-Methylene-bis-(2-Chloroaniline)	mg/kg	N.D.	
	4,4'-oxydianiline	mg/kg	N.D.	
	4,4'-thiodianiline	mg/kg	N.D.	
	o-Toluidine	mg/kg	N.D.	
	2,4-toluyldiamine	mg/kg	N.D.	
	2,4,5-Trimethylaniline	mg/kg	N.D.	
o-anisidine	mg/kg	N.D.		
4-aminoazobenzene	mg/kg	N.D.		
2,4-xylidine	mg/kg	N.D.		
2,6-xylidine	mg/kg	N.D.		

N.D.= Not Detected
 Detection limits: 5 mg/kg.



Zhejiang Garment and Textile Fabric Products Quality Inspection Center

TEST REPORT

No. NKAQ20052589

Page 3 of 3

Items	Unit	Requirements	Results	Conclusions
Fibre content	%	—	Nylon: 75.3 Spandex: 24.7	—
Formaldehyde	mg/kg	≤ 20	N.D. (limits: 20)	Pass
pH	—	4.0~8.5	6.5	Pass
Maximum force	N	≥ 20	230	Pass

This space intentionally left blank.

